



上海宝钢汽车板有限公司
SHANGHAI BAOSTEEL NOVA AUTOMOTIVE
STEEL SHEETS CO.,LTD.

产品质量证明书
INSPECTION CERTIFICATE

上海市宝山钢铁股份有限公司厂区内纬
五路冷轧综合楼 邮编200941
Cold Rolling Comprehensive Building,
Wei Wu Road,Baosteel,Baoshan District
200941 Shanghai,P.R.CHINA
TEL (021)26648888 FAX (021)26643880

订货单位 CUSTOMER																产品名称 PRODUCT		热镀锌钢带																	
收货单位 PURCHASER																代 号 CUSTOMER'S NO.				证书号 CERTIFICATE NO.															
标 准 SPECIFICATION		Q/BQB 420-2023 HC420LAD+Z 40/40-M-FC-O PT.A-PW.A-PF.A														客户订单编号 CUSTOMER ORDER NO						签发日期 DATE OF ISSUE		2026/04/21		合同号 MILL'S NO.									
																许可证号 LICENSE NO.																			
序 号 NO.	钢卷 /捆包号 COIL/PACK NO.	件 数 QTY	炉 号 HEAT NO.	规格及重量 MATERIAL DESCRIPTION					化学成分 CHEMICAL COMPOSITION % *0 (1=x10 2=x100 3=x1000 4=x10000 5=x100000)										拉伸试验 TENSILE TEST (G.L= L 3 , *02= 2)					*01 弯 曲	硬度 HARD NESS	镀层重量 COATING MASS									
				厚度 THICK	宽度 WIDTH	长度 LENGTH	张 数 SHEETS	重量 MASS (kg)	C 3	Si 3	Mn 2	P 3	S 3	Al 3	Ti 2	Nb 3			屈服 Y.S.	抗拉 T.S.	伸长 EL					两面 BOTH	上面 TOP	下面 BOT							
				mm															MPa	%	值	值			g/m²										
1		1	16275912	1.20	1250	COIL	1	8930	67	21	80	23	5	32	0	45			453	510	28					85.0	43.0	42.0							
合计 Total				1 8930																															
备 注 REMARKS																																			
注 释 NOTES				Y.S.= YIELD STRENGTH T.S.= TENSILE STRENGTH EL= ELONGATION G.L.= GAUGE LENGTH L1= 5.65SQRT(FO) L2= 50MM L3= 80MM *0：熔炼分析 HEAT ANALYSIS *01:COATING BEND TEST *02方向 ORIENTATION 1=纵向 LONGI 2=横向 TRANS 4= 45 ° TO THE ROLLING DIRECTION																															
会验者 SURVEYOR TO				本产品已按上述要求进行制造和检验，其结果符合要求，特此证明。																								Luo Wengjin 公司总经理 PRESIDENT 罗文敬							
				WE HEREBY CERTIFY THAT MATERIAL DESCRIBED HEREIN HAS MANUFACTURED AND TESTED WITH SATISFACTORY RESULTS IN ACCORDANCE WITH THE REQUIREMENTS OF THE ABOVE MATERIAL SPECIFICATION.																															